

Score-TRICENTRIC® PRESSURE/TEMPERATURE RATING - CLASS 150		
Maximum Temperature Of	Working Pressure, psig	
	Carbon Steel	316SS
-20 to 100	285	275
200	260	235
300	230	215
400	200	195
500	170	170
600	140	140
650	125	125
700	110	110
750	95	95
800	80	80
850	Note A	65
900	–	50
950	–	35
1000	–	20

Note A: Permissible, but not recommended for prolonged usage above about 800°F.