

<b>Score-TRICENTRIC® Pressure/Temperature Rating- Class 300</b>		
Maximum Temperature Of	Working Pressure, psig	
	Carbon Steel	316SS
-20 to 100	740	720
200	675	620
300	655	560
400	635	515
500	600	480
600	550	450
650	535	440
700	535	435
750	505	425
800	Note A	420
850	-	420
900	-	415
950	-	385
1000	-	365
1050	-	360
1100	-	305
1150	-	235
1200	-	185
1250	-	145
1300	-	115
1350	-	95
1400	-	75
1450	-	60
1500	-	40

Note A:

Permissible, but not recommended for prolonged use above 800 degrees F